

sub B1
A1
C1
a water soluble polymer,

wherein the film is breathable and has a water vapor transmission rate greater than about 1500 g/m²/24hrs;

further wherein the film is porous and wettable and has an elongation at break of greater than about 100%.
